

Technical Datasheet

- Grade Name: LDPE 0075
- o Categories: Polymer, Thermoplastic, Polyethylene, Low Density Polyethylene
- Processing Methods: Film
- Applications: Carrier bags, Shrink film, Industrial film, Dust bin liners, Large bottles, Blow molding of small containers, Packaging of pharmaceutical products, Packaging of foodstuffs and Bottles for storage of chemical products
- Features: Excellent yield and tensile strength, High stiffness

Physical Properties			
Properties	Value	Unit	Test Method
MFI(190°C/2.16 KG)	0.75	g/10min	ISO 1133
Density	0.920	g/cm³	ISO 1183
Mechanical Properties			570
Properties	Value	Unit	Test Method
Dart Impact	120	gr	ASTM D 1709
Elongation at Break, MD	300	%	ASTM D 882
Elongation at Break, TD	450	%	ASTM D 882
Tensile at Break, MD	170	Kg/cm ²	ASTM D 882
Thermal Properties			
Properties	Value	Unit	Test Method
H.D.T.	33	°C	ASTM D 648
Vicat Softening Point	95	°C	ASTM D1525

Typical Properties: These values are not to be considered as product specifications.

This document is issued by the Company subject to its general condition of service printed overieaf. Attention is drawn to the limitations of liability identification and jurisdictional issues defined therein.

 +981142434507
NO.9 Beshel Industrial City, Shirgah, Mazandaran, Iran

