

Technical Datasheet

- **Grade Name:** LDPE 2420 D
- **Categories:** Polymer, Thermoplastic, Polyethylene, Low Density Polyethylene
- **Processing Methods:** Blown Film
- **Applications:** Film, Heavy-Duty Sacks, Shrink Films
- **Features:** Good Shrink Properties, Good Processability, Good Drawdown Ability, Good Toughness, Good Tear Strength

Physical Properties			
Properties	Value	Unit	Test Method
MFI(190°C/2.16 KG)	0.25	g/10min	ISO 1133
Density	0.923	g/cm ³	ISO 1183
Mechanical Properties			
Properties	Value	Unit	Test Method
Film Elongation at Break, MD	200	%	ISO 527
Film Elongation at Break, TD	500	%	ISO 527
Tensile Modulus	240	MPa	ISO 527
Film Tensile Strength at Break, MD	27	MPa	ISO 527
Film Tensile Strength at Break, TD	20	MPa	ISO 527
Tensile Strength at Yield	10	MPa	ISO 527
Dart Drop Impact (50 blown film)	250	g	ASTM D1709
Thermal properties			
Vicat Softening Temp (A50 (50°C/h 10N))	94	°C	ISO 306
Optical Properties			
Properties	Value	Unit	Test Method
Gloss (60°C, 50)	>50		ASTM D2457
Haze (50)	<14	%	ASTM D1003

Typical Properties: These values are not to be considered as product specifications.

This document is issued by the Company subject to its general condition of service printed overleaf. Attention is drawn to the limitations of liability identification and jurisdictional issues defined therein.

+981142434507

NO.9 Beshel Industrial City,
Shirgah, Mazandaran, Iran

