

## Technical Datasheet

- **Grade Name:** PP 552 RMP
- **Categories:** Polymer, Thermoplastic, Polypropylene, Polypropylene Homopolymer
- **Processing Methods:** Fiber Extrusion (CF, BCF, staple)
- **Applications:** Nonwoven fabrics for diapers, medical-sanitary applications, Wipes and tissues, Straps for backpacks, sport bags, bulk bags and for safety belts, Upholstery and sportswear, Bulk continuous filament for carpets, Nonwoven staple fiber, Hygiene nonwoven
- **Features:** High melt flow, Excellent antigasfading properties, Good processability, Homopolymer

Physical Properties			
Properties	Value	Unit	Test Method
MFI( 230 °C/2.16 Kg)	25	g/10min	ISO 1133
Density	0.9	g/cm <sup>3</sup>	ISO 1183
Mechanical Properties			
Properties	Value	Unit	Test Method
Flexural Modulus	1500	MPa	ASTM D790
Izod Impact Strength, Notched	30	J/m	ASTM D256
Tensile Elongation at Yield	13	%	ASTM D638
Hardness, Rockwell R	100	R Scale	ASTM D785
Tensile Strength at Yield	32	MPa	ASTM D638
Thermal Properties			
Properties	Value	Unit	Test Method
H. D. T (0.46 MPa)	94	°C	ASTM D648
Oven Aging ( 150 °C, Air)	150	h	ASTM D3012
Vicat Softening Point (10N)	152	°C	ASTM D1525

Typical Properties: These values are not to be considered as product specifications.

This document is issued by the Company subject to its general condition of service printed overleaf. Attention is drawn to the limitations of liability identification and jurisdictional issues defined therein.

+981142434507

NO.9 Beshel Industrial City,  
Shirgah, Mazandaran, Iran

